

Product Description

Bayblock Prime NR is a water-based two component epoxy primer without rust inhibitors. It has exceptional adhesion to metal substrates including aluminum as well as asphaltic surfaces. This two-component product provides the adhesion of a solvent-based epoxy with water clean up. Bayblock Prime NR provides an exceptional surface for the application of polyurethane foam or elastomeric coatings.

Application and Handling

Thoroughly mix one (1) part curing agent to five (5) parts resin by volume (0.83 gal to 4.17 gal.) If material viscosity is too high for spray equipment, dilution up to 5% may be necessary. Do not dilute more than one (1) quart for every five gallons.

Bayblock Prime NR may be applied by conventional airless spray equipment, medium nap rollers or brushes. Airless spray application is most efficient whereas rolling or brushing may be used for touch up, flashing and edge terminations or to fill voids, pinholes, holidays or cracks. CONTACT BAYSYSTEMS TECHNICAL PERSONNEL FOR SPECIFIC RECOMMENDATIONS, PRICING AND AVAILABILITY OF SPRAY AND AUXILIARY EQUIPMENT.

Apply Bayblock Prime NR only to clean, dry, sound surfaces free of loose particles, rust, or other foreign matter. Apply only to roofs that have adequate positive drainage (i.e., a minimum slope of 1/4 inch per foot). A test patch is always recommended.

It is recommended that Bayblock Prime NR be spray applied in multi-directional (north-south/east-west) passes to ensure uniform film build and to avoid pinholing. Final cured dry film thickness must be free of holidays, cracks or blisters. COATING APPLICATION MUST BE SUSPENDED IMMEDIATELY AND Baysystems TECHNICAL SERVICE PERSONNEL CONTACTED IF THE RESULTS OBTAINED ARE LESS THAN DESIRABLE.

The recommended application rate is 1/3 gallon per 100 s.f.

Limitations and Precautions

Do not apply Bayblock Prime NR when temperatures fall below 50°F or when there is a possibility of temperatures dropping below 40°F within a 24 hour period after application. Do not apply over wet substrates or when inclement weather is imminent. High relative humidity will retard drying.

NOTE: Application and drying of any product can reduce the temperature by as much as 20°F due to evaporative cooling (i.e., applying water based material at 50°F can result in a 30°F temperature).

It is extremely important that Bayblock Prime NR is totally cured before proceeding. Total cure may be prolonged drastically by high humidity and cool ambient temperatures.

Discard unused portion of mixture after four hours. Material may appear normal, but physical properties will be adversely affected after the end of pot life.

Typical Physical Properties

Property	Value
Solids by Weight:	55 ± 2%
Solids by Volume	40 ± 2%
Theoretical Coverage :	300 s.f./gal.
Weight per gallon:	10.5 lbs./gal.
Recommended Service Temperature:	>50°F
Number of Components:	Two
Color:	Orange
Pot Life:	4 hours

Wet Physical Characteristics

Mix Ratio:	1:5
Flash Point:	>250°
Shelf Life:	12 month if properly stored
Clean Up:	Water
Thinner:	Not Recommended

Product Reactivity

Dry Time:	30 Minutes
Recoat:	3 Hours dependant on environmental and substrate conditions

Bayblock™ Prime NR

General Safety, Toxicity, Health Data (continued)

CONTAMINATION: Avoid moisture contamination in containers. Containers should not be released if contaminated. Do not attempt to use contaminated materials.

EYE PROTECTION: Safety glasses, goggles, or a face shield are recommended.

SKIN PROTECTION: Chemical resistant gloves are recommended. Cover as much of the exposed skin area as possible with appropriate clothing.

RESPIRATORY PROTECTION is MANDATORY! Respiratory protective equipment, impervious foot wear and protective clothing are required at all times during spray application. Contact BaySystems for a copy of the Model Respiratory Protection Program developed by API.

INGESTION: Do not take internally.

Consider the application and environmental concentrations in deciding if additional protective measures are necessary.

Disclaimer

The data presented herein is not intended for non-professional applicators or those persons who do not purchase or utilize this product in the normal course of their business.

The potential user must perform any pertinent tests in order to determine the product's performance and suitability in the intended application, since final determination of fitness of the product for any particular use is the responsibility of the buyer. The aforementioned data on this product is to be used as a guide and is subject to change without notice.

The sole exclusive remedy of buyer, which is to have Bayer MaterialScience replace any nonconforming product at no cost to buyer is conditioned upon buyer notifying Bayer MaterialScience or its distributor in writing of such defect within thirty days of the discovery of such defect. Bayer MaterialScience shall not be liable for any direct, incidental or consequential damages resulting from any breach of warranty.

Bayer MaterialScience has no role in the manufacture of the finished polymer membrane other than to supply its two components. It is vital that the person applying this product understands the product and is fully trained and certified in the use of plural component equipment. The quality and fitness of the product is dependent upon the proper mixture and application of the components by the applicator. There are no warranties that extend beyond the description on the face of this instrument. Bayer MaterialScience warrants only that the two components of this product shall conform to the technical specifications published in the product literature.

Bayer MaterialScience makes no warranty as to the quality of any product modified, supplemented, tinted, or altered in any way after it leaves the manufacturing plant. Bayer MaterialScience does not warrant that this product is suitable for use as a liner for potable water containers. Use of this product in a potable water container could be hazardous to health if it is improperly processed or applied.

The liability of Bayer MaterialScience for any nonconformity of this product to its technical specifications shall be limited to replacement of the product.

The information herein is believed to be reliable, but unknown risks may be present. BAYER MATERIALSCIENCE MAKES NO WARRANTIES,

EXPRESSED OR IMPLIED, INCLUDING PATENT WARRANTIES OR WARRANTIES OF MERCHANTABILITY OR FITNESS OF USE, WITH RESPECT TO PRODUCTS OR INFORMATION SET FORTH HEREIN. Nothing contained herein shall constitute permission or recommendation to practice any invention covered by a patent without a license from the owner of the patent.

Accordingly, the buyer assumes all risks whatsoever as to the use of these materials and buyer's exclusive remedy as to any breach of warranty, negligence, or other claim shall be limited to the purchase price of the materials. Failure to adhere to any recommended procedures shall relieve Bayer MaterialScience of all liability with respect to the materials and the use thereof.

East Office
2400 Spring Stuebner Road
Spring, TX 77389
1.800.221.3626
Tel 281.350.9000
Fax 281.288.6450

West Office
PO Box 6460
Phoenix, AZ 85005
1.800.289.8272
Tel 602.269.9711
Fax 602.269.9115

baysystemsspray.com



©2008 Bayer MaterialScience. All rights reserved.